



Art Of Fibre
Hoofdstraat 152
6061CH Posterholt
The Netherlands
esther@artoffibre.com

Customer
GG Ramseyer Becanson

OFDA Test Report

OFDA2220 v5.423 (Cal:4.8483W-2.37), Measured: 26Jun25, File: 2220_250626_201735.MES

Name : Medellin
Description : Certified Alpaca Testing
Operator : Esther Verbeek
Lot/client : GG Ramseyer Besancor

Diameter : 16.3 μm
SD : 3.8 μm
CV : 23.4 %
CE : 8.2 μm
Comfort : 100.0 %
%<15 μm : 35.6 %
Spin fineness : 16.2
Curve : 38.8 deg/mm
Curve SD : 30.3 deg/mm
Num fibres : 2049

Staple length : 100.0 mm
Finest from tip : 0.0 mm
Mean diam ends : 16.0 μm
Skin diam : 16.3 μm
Min diam : 15.7 μm
Max diam : 17.6 μm
SD Along : 0.6 μm
SD Across : 4.8 μm

