



Art Of Fibre
Hoofdstraat 152
6061CH Posterholt
The Netherlands
esther@artoffibre.com

Customer
GG Ramseyer Becanson

OFDA Test Report

OFDA2220 v5.423 (Cal:4.8483W-2.37), Measured: 26Jun25, File: 2220_250626_201735.MES

Name : Jellinek
Description : Certified Alpaca Testing
Operator : Esther Verbeek
Lot/client : GG Ramseyer Besancor

Diameter : 20.2 μm
SD : 4.4 μm
CV : 21.6 %
CE : 8.8 μm
Comfort : 97.6 %
%<15 μm : 6.5 %
Spin fineness : 19.7 μm
Curve : 41.3 deg/mm
Curve SD : 29.9 deg/mm
Num fibres : 1982

Staple length : 90.0 mm
Finest from tip : 80.0 mm
Mean diam ends : 20.1 μm
Skin diam : 20.1 μm
Min diam : 18.7 μm
Max diam : 22.1 μm
SD Along : 0.9 μm
SD Across : 4.8 μm

