



Art Of Fibre
Hoofdstraat 152
6061CH Posterholt
The Netherlands
esther@artoffibre.com

Customer
GG Ramseyer Becanson

OFDA Test Report

OFDA2220 v5.423 (Cal:4.8483W-2.37), Measured: 26Jun25, File: 2220_250626_201735.MES

Name : Soleurt
Description : Certified Alpaca Testing
Operator : Esther Verbeek
Lot/client : GG Ramseyer Besancor

Diameter : 19.1 μm
SD : 4.2 μm
CV : 22.1 %
CE : 8.8 μm
Comfort : 97.3 %
%<15 μm : 9.9 %
Spin fineness : 18.7 μm
Curve : 45.3 deg/mm
Curve SD : 32.9 deg/mm
Num fibres : 1969

Staple length : 85.0 mm
Finest from tip : 35.0 mm
Mean diam ends : 19.6 μm
Skin diam : 19.2 μm
Min diam : 18.5 μm
Max diam : 20.2 μm
SD Along : 0.6 μm
SD Across : 4.9 μm

